

CHEMICAL CHART

A - No Effect - Acceptable
 B - Minor Effect - Acceptable
 C - Moderate Effect - Questionable
 D - Severe effect - Not Recommended

	302 Stainless Steel	304 Stainless Steel	316 Stainless Steel	440 Stainless Steel	Aluminium	Titanium	Hastelloy C	Cast Bronze	Brass	Cast Iron	Carbon Steel	PVC (Type 1)	Tygon E-3606	Teflon	Noryl	Polyacetal	Nylon	Cyclac (ABS)	Polyethylene	Polypropylene	Ryton	Carbon	Ceramic	Ceramagent A	Viton	Buna Nitrile	Silicon	Neoprene	Ethylene P. EPDM	Rubber (Natural)	Epoxy	
Acetaldehyde 5	A	A	A	-	B	A	A	D	-	-	C	D	D	A	-	A	A	D	C	B	A	A	A	-	A	B	B	D	B	C	A	
Acetamide	-	B	A	-	-	-	-	-	-	-	C	-	-	-	-	B	-	-	-	-	-	-	A	-	A	A	-	A	A	D	A	
Acetate Solv. 2	A	B	A	B	B	-	-	A	C	B	A	B	D	A	-	-	A	-	B	D	-	A	A	-	D	D	-	D	-	-	A	
Acetic Acid, Glacial 1	-	B	A	A	B	A	A	C	C	D	A	C	B	A	C	D	D	D	B	B	A	A	A	-	D	D	B	C	B	C	B	
Acetic Acid 20%	-	-	A	-	-	A	A	-	C	-	-	B	-	A	A	-	D	-	-	A	A	-	A	-	D	C	-	C	-	-	B	
Acetic Acid 80%	-	-	A	-	-	A	A	-	C	-	-	D	-	A	B	-	D	-	-	B	-	-	A	-	D	C	-	D	-	-	B	
Acetic Acid	-	B	A	B	B	A	A	C	C	D	C	A	B	A	A	D	D	C	B	A	A	A	A	-	C	C	-	C	B	C	A	
Acetic Anhydride	B	A	A	B	B	A	A	C	D	B	D	D	D	A	D	D	D	D	A	A	A	A	A	-	D	A	C	B	B	C	A	
Acetone 6	A	A	A	B	A	A	A	A	A	A	A	D	D	A	D	B	A	D	C	B	A	A	A	A	D	D	B	C	A	D	B	
Acetyl Chloride	-	C	A	-	-	-	-	D	-	-	-	-	-	A	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	A	
Acetylene 2	A	A	A	A	A	-	-	B	-	A	A	B	-	-	-	A	A	-	-	D	A	A	A	-	A	A	C	B	A	C	A	
Acrylonitrile	A	A	C	-	B	-	B	A	-	C	-	-	-	-	-	B	-	D	-	B	A	A	A	-	C	D	-	D	-	-	A	
Alcohols																																
Amyl	A	A	A	-	C	A	A	A	B	C	C	A	B	A	C	A	A	B	B	B	A	A	A	-	A	A	D	A	A	C	A	
Benzyl	-	A	A	-	B	A	A	A	C	-	-	D	B	-	A	A	A	D	D	A	-	A	A	-	A	A	-	B	B	D	A	
Butyl	A	A	A	-	B	B	A	B	C	C	C	A	B	A	A	A	A	-	B	B	A	A	A	-	A	A	D	A	A	A	A	
Diacetone 2	-	A	A	-	A	A	A	A	C	-	A	D	-	-	A	A	A	-	-	D	-	A	A	-	D	D	-	D	A	D	A	
Ethyl	-	A	A	A	B	A	A	A	C	A	A	A	C	-	A	B	A	B	B	A	-	A	A	A	A	A	A	B	A	B	A	A
Hexyl	-	A	A	-	A	A	A	A	C	-	A	A	-	-	A	A	A	-	-	A	-	A	A	-	A	A	D	B	A	A	A	
Isobutyl	-	A	A	-	B	A	A	A	C	-	A	-	-	-	A	A	A	B	-	-	-	A	A	-	A	C	B	A	A	A	A	
Isopropyl	-	A	A	-	B	A	A	A	C	C	A	-	-	-	A	A	A	-	-	A	-	A	A	-	A	C	C	B	A	A	A	
Methyl 6	-	A	A	A	B	A	A	A	C	A	A	B	-	A	A	C	A	D	B	A	-	A	A	A	C	B	-	A	A	A	A	
Octyl	-	A	A	-	A	A	A	A	C	-	A	-	-	-	A	A	A	-	-	-	-	A	A	-	A	B	-	B	A	C	A	
Propyl	-	A	A	-	A	A	A	A	-	-	A	A	-	A	A	A	A	-	-	A	-	A	A	-	A	A	B	A	A	A	A	
Aluminum Chloride 20%	-	D	C	D	B	A	A	D	-	D	A	A	B	-	A	C	A	-	B	A	A	A	A	-	A	A	-	A	A	A	A	
Aluminum Chloride	C	D	C	-	D	C	A	C	-	D	B	A	A	A	A	-	D	-	-	A	A	A	A	-	A	A	C	A	-	-	A	
Aluminum Flouride	-	D	C	D	-	D	B	-	-	-	A	A	-	A	A	C	D	-	B	A	-	A	-	-	A	A	C	A	-	C	A	
Aluminum Hydroxide 6	-	A	A	A	A	-	-	A	-	D	A	A	-	A	A	B	A	-	-	A	-	A	A	A	A	A	A	-	A	-	A	A
Alum Potassium Sulfate (ALUM),10%	-	A	-	-	A	-	B	-	-	D	A	A	-	A	-	-	A	-	A	-	-	A	A	-	A	-	-	A	-	-	A	A
Alum Potassium Sulfate (ALUM) 100%	-	D	A	B	B	-	B	C	-	-	A	A	B	A	A	C	D	-	B	A	-	A	A	-	A	A	-	A	-	-	A	A
Aluminum Sulfate	-	C	C	A	A	A	A	C	C	D	A	A	B	A	A	C	A	-	B	A	A	A	A	-	A	A	-	A	A	A	A	
Amines	A	A	A	-	A	B	A	B	-	A	B	C	A	A	B	D	A	-	-	-	-	A	A	-	D	D	C	B	B	C	A	
Ammonia 10%	-	-	A	-	-	A	A	-	-	-	-	A	-	A	A	-	A	-	-	A	A	-	A	-	A	D	-	A	-	-	B	
Ammonia Anhydrous	A	B	A	A	B	B	A	D	-	D	B	A	B	A	A	D	A	-	B	A	B	C	A	-	D	B	B	A	A	D	A	
Ammonia, Liquids	-	A	A	A	D	-	B	D	-	A	A	A	B	A	A	D	-	-	D	A	-	A	A	-	D	B	B	A	A	D	A	
Ammonia, Nitrate	-	A	A	A	C	-	-	D	-	-	A	B	B	-	A	C	-	-	-	A	-	A	A	-	-	A	-	C	-	-	A	
Ammonium Bifluoride	-	C	A	-	D	-	B	-	-	-	-	A	-	-	A	D	-	-	-	A	-	-	A	-	A	A	-	A	-	-	A	
Ammonium Carbonate	B	A	A	A	C	A	B	B	-	C	B	A	B	A	A	D	A	-	-	A	-	A	A	-	B	D	C	A	A	-	A	
Ammonium Casenite	-	-	A	-	-	-	-	-	-	-	-	-	-	-	A	D	-	-	-	-	-	-	-	-	-	-	-	-	-	-	A	
Ammonium Chloride	C	A	C	A	C	A	A	D	C	D	D	A	B	A	A	B	A	-	B	A	A	A	A	-	A	A	C	A	A	A	A	
Ammonium Hydroxide	A	A	A	A	C	A	A	D	D	A	C	A	B	A	A	D	A	B	B	A	A	A	A	-	B	B	B	A	A	C	A	
Ammonium Nitrate	A	A	A	A	B	A	A	D	D	A	D	A	B	A	A	C	D	-	B	A	A	A	A	-	A	A	C	A	A	A	A	
Ammonium Oxalate	-	A	A	A	-	-	A	-	-	-	A	-	-	-	-	B	-	-	-	-	-	-	-	-	-	-	-	-	-	-	A	
Ammonium Persulfate	-	A	A	A	C	A	A	A	-	D	A	A	-	A	A	D	D	-	-	A	-	A	A	-	C	A	-	A	A	A	A	

	302	304	316	440	Aluminium	Titanium	Hastelloy C	Cast Bronze	Brass	Cast Iron	Carbon Steel	PVC (Type 1)	Tygon E-3606	Teflon	Noryl	Polycetal	Nylon	Cyclac (ABS)	Polyethylene	Polypropylene	Ryton	Carbon	Ceramic	Ceramagent A	Viton	Buna Nitrile	Silicon	Neoprene	Ethylene P. EPDM	Rubber (Natural)	Epoxy	
Ammonium Phosphate, Dibasic	B	A	A	A	B	A	A	C	-	-	D	A	-	A	A	B	A	-	B	A	-	A	A	-	A	A	B	A	A	A	A	
Ammonium Phosphate, Monobasic	-	A	A	A	B	A	A	D	-	-	A	A	A	A	A	B	A	-	B	A	-	A	A	-	A	A	B	A	A	A	A	
Ammonium Phosphate, Tribasic	B	A	A	A	B	A	A	C	-	C	D	A	-	A	A	B	A	-	B	A	-	A	A	-	A	A	B	A	A	A	A	
Ammonium Sulfate	C	A	B	A	B	A	A	B	C	C	C	A	D	A	A	B	D	-	B	A	A	A	A	-	D	A	B	A	A	A	A	
Ammonium Thio-Sulfate	-	-	A	-	-	A	-	-	-	D	A	-	-	-	-	B	-	-	-	-	-	A	A	-	-	A	-	A	-	-	A	
Amyl-Acetate	B	A	A	C	B	A	A	C	-	-	C	D	D	A	D	A	B	-	D	D	A	A	A	-	D	D	D	D	A	D	A	
Amyl Alcohol	-	A	A	-	B	A	A	A	-	-	A	A	B	A	C	A	A	-	B	A	-	A	A	-	B	B	D	A	A	C	A	
Amyl Chloride	-	C	B	-	D	-	A	A	-	-	A	D	C	A	D	A	C	-	D	D	-	A	A	-	A	D	-	D	D	D	A	
Aniline	B	A	A	A	C	C	B	C	-	-	C	D	D	A	D	D	C	D	C	B	A	A	A	-	D	D	C	D	B	D	A	
Anti-Freeze	-	A	A	-	A	-	A	B	B	B	C	A	B	A	A	A	A	B	B	A	A	A	A	A	A	A	C	A	A	A	A	
Antimony Trichloride	-	D	D	-	D	-	A	-	-	-	-	A	A	A	-	-	D	-	A	-	-	-	A	-	-	-	-	C	-	A	A	
Aqua Regia (80%, HCl, 20%, HNO)	-	D	D	-	D	A	D	D	-	-	-	D	D	A	D	D	D	-	D	C	-	-	D	-	C	D	C	D	D	D	D	
Arochlor 1248	-	-	-	-	-	-	-	-	-	-	A	-	-	-	D	-	-	-	-	-	-	-	A	-	-	A	D	-	D	B	D	A
Aromatic Hydrocarbons	-	-	A	-	A	-	-	A	-	A	A	D	-	-	D	A	-	-	C	-	-	A	-	-	A	D	-	D	D	D	A	
Arsenic Acid	B	A	A	-	D	-	-	D	B	D	D	A	B	A	A	D	A	-	B	A	-	A	A	-	A	A	-	A	-	C	A	
Asphalt	-	B	A	-	C	-	-	A	-	C	-	A	-	-	-	A	A	-	-	A	A	-	A	A	B	C	B	D	D	A		
Barium Carbonate	B	A	A	A	B	A	A	B	-	B	B	A	A	A	A	A	A	-	B	A	-	A	A	A	A	A	-	A	-	A	A	
Barium Chloride	C	A	A	A	D	A	A	B	-	N	C	A	B	A	A	A	B	-	B	A	A	A	A	-	A	A	B	A	A	A	A	
Barium Cyanide	-	-	A	-	-	-	-	C	-	-	A	-	-	-	-	B	-	-	B	-	-	A	-	-	A	C	-	A	A	-	A	
Barium Hydroxide	B	C	A	A	D	B	B	B	-	C	C	A	-	A	A	D	A	-	B	A	A	A	A	A	A	A	C	A	A	A	A	
Barium Nitrate	-	A	A	-	-	A	-	D	-	A	A	B	-	-	A	A	-	-	-	-	-	-	A	A	-	A	A	-	A	A	-	B
Barium Sulfate	B	A	A	A	D	A	A	C	-	C	C	A	-	A	A	A	A	-	B	A	A	A	B	-	A	A	D	A	A	-	B	
Barium Sulfide	B	A	A	-	D	-	-	C	-	C	C	A	A	A	A	A	A	-	B	A	-	A	A	-	A	A	C	A	A	A	A	
Beer 2	A	A	A	-	A	A	A	A	B	D	D	A	-	A	A	B	D	B	B	D	-	A	A	-	A	D	C	A	A	A	A	
Beet Sugar Liquids	A	A	A	-	A	-	-	A	B	A	-	A	-	A	A	B	A	B	-	A	-	A	A	-	A	A	-	B	A	A	A	
Benzaldehyde 3	A	A	A	-	B	A	A	A	-	B	A	D	D	A	D	A	C	D	D	D	A	A	A	-	D	D	B	D	A	D	A	
Benzene 2	B	A	A	A	B	A	B	B	A	B	C	D	C	A	D	A	A	D	D	D	A	A	A	A	A	D	-	D	D	D	A	
Benzoic Acid 2	B	A	A	A	B	A	A	B	-	D	-	A	B	A	A	B	D	-	B	D	-	A	B	-	A	D	-	D	D	D	A	
Benzol	-	A	A	-	B	A	A	B	A	-	-	D	-	A	D	A	A	-	-	A	-	A	A	A	D	D	-	D	-	-	A	
Borax (Sodium Borate)	-	A	A	A	C	-	A	A	B	A	C	A	A	A	A	A	A	-	B	A	A	A	A	A	A	B	C	A	A	C	A	
Boric Acid	B	A	A	A	B	A	A	B	C	D	-	A	B	A	A	A	A	-	B	A	-	A	A	A	A	A	-	A	A	A	A	
Brewery Slop	-	-	A	-	-	-	-	A	-	A	-	-	-	-	-	A	-	-	-	-	-	-	A	A	-	A	A	-	-	-	A	
Bromine 2(Wet)	D	D	D	D	D	A	A	C	-	D	D	B	B	A	D	D	D	D	D	D	D	D	D	A	D	A	D	D	D	D	C	
Butadiene	A	A	A	-	A	-	-	C	A	C	C	A	-	A	-	A	A	-	-	-	-	B	A	A	-	A	A	-	B	A	-	A
Butanes 2 1	A	A	A	-	A	-	-	A	A	C	C	A	C	A	D	A	A	B	C	D	A	A	A	-	A	A	D	B	D	D	A	
Butanol	-	A	A	-	A	-	A	A	-	-	-	-	-	A	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
Butter	B	B	A	-	A	-	-	D	-	D	-	-	B	-	B	A	-	B	-	-	-	A	A	-	A	A	-	B	A	D	A	
Buttermilk	C	A	A	A	A	-	-	D	-	D	-	-	B	A	A	A	A	B	-	-	-	-	A	A	-	A	A	-	A	-	D	A
Butylene	-	-	A	-	A	-	-	A	A	A	A	B	-	A	-	A	-	-	-	-	-	A	A	-	A	B	-	-	D	D	A	
Butyl Acetate 1	-	-	C	-	A	-	A	A	-	-	A	D	D	A	D	A	-	-	C	D	A	A	A	-	D	B	D	D	B	D	A	
Butyric Acid 1	B	B	A	A	B	A	A	C	-	D	-	B	-	A	A	C	D	D	-	A	-	A	D	-	D	D	-	D	B	-	A	
Calcium Bisulfate	C	D	A	-	D	-	-	D	D	D	-	A	A	A	-	-	A	-	-	-	-	-	-	-	A	A	C	C	-	A	A	
Calcium Bisulfide	-	-	B	-	C	A	A	C	-	-	-	A	-	A	A	D	A	-	B	A	-	A	A	-	A	A	-	A	D	-	A	
Calcium Bisulfite	-	D	A	-	C	A	A	C	-	-	-	A	-	A	A	-	A	-	-	-	-	-	-	-	A	A	-	A	-	-	-	
Calcium Carbonate	B	A	A	A	C	A	A	C	-	D	-	A	A	A	A	A	A	-	B	A	-	A	A	-	A	A	-	A	-	A	A	
Calcium Chlorate	-	C	A	-	-	-	B	C	-	-	-	A	A	A	-	-	A	-	A	-	-	-	-	-	-	-	-	-	-	-	A	
Calcium Chloride	C	A	D	C	C	A	A	B	-	C	-	A	A	A	A	D	A	B	B	A	A	A	A	B	A	A	B	D	A	A	A	
Calcium Hydroxide	B	A	A	-	C	A	A	B	-	-	-	A	A	A	A	B	A	-	B	A	-	A	A	A	A	A	C	A	A	A	A	
Calcium Hypochlorite	D	A	C	C	C	A	B	D	-	D	-	D	-	A	A	D	D	-	B	A	-	A	A	-	A	B	C	D	A	C	A	
Calcium Sulfate	B	A	A	A	B	A	B	B	-	-	-	A	A	A	A	A	A	C	B	A	A	A	A	-	A	A	-	D	-	C	A	
Calgon	-	A	A	-	-	-	-	C	-	D	-	-	-	-	A	B	-	-	-	-	-	A	-	-	A	-	-	-	-	-	A	
Cane Juice 2	-	A	A	-	B	-	-	B	C	A	-	A	-	-	-	A	A	-	-	-	-	D	-	A	-	-	-	-	-	-	A	

	302	304	316	440	Aluminium	Titanium	Hastelloy C	Cast Bronze	Brass	Cast Iron	Carbon Steel	PVC (Type 1)	Tygon E-3606	Teflon	Noryl	Polyacetal	Nylon	Cyclocac (ABS)	Polyethylene	Polypropylene	Ryton	Carbon	Ceramic	Ceramagent A	Viton	Buna Nitrile	Silicon	Neoprene	Ethylene P. EPDM	Rubber (Natural)	Epoxy			
Ethylene Chloride 2	-	A	A	-	C	B	B	A	-	C	C	D	-	A	D	A	-	D	-	D	A	A	A	-	A	D	D	D	C	D	A			
Ethylene Dichloride	-	A	A	-	D	A	B	C	-	-	C	D	D	A	D	A	A	-	D	A	A	C	A	-	A	D	D	D	C	D	A			
Ethylene Glycol 4	-	A	A	-	A	-	A	B	B	B	C	A	B	A	A	A	A	B	B	A	A	A	A	A	A	A	C	A	A	A	A			
Ethylene Oxide	-	-	A	-	A	-	-	A	-	-	-	D	-	A	A	A	A	-	-	-	-	A	A	-	D	D	D	D	C	D	A			
Fatty Acids	-	A	A	-	B	A	A	C	-	D	-	A	B	A	B	A	A	-	B	A	-	A	A	-	A	C	C	B	C	C	A			
Ferric Chloride	-	D	D	D	D	A	B	D	D	D	-	A	B	A	A	B	D	-	B	A	A	A	A	-	A	D	C	B	A	A	A			
Ferric Nitrate	-	A	A	A	D	A	A	D	-	-	-	A	-	A	A	B	D	-	B	A	A	A	A	-	A	A	D	A	A	A	A			
Ferric Sulfate	-	A	C	A	D	A	A	D	D	D	-	A	B	A	A	B	A	C	-	A	A	C	A	-	A	B	C	A	-	A	A			
Ferrous Chloride	-	D	D	-	D	A	B	C	-	D	-	A	B	A	A	B	D	-	B	A	A	A	A	-	A	B	C	A	-	A	A			
Ferrous Sulfate	B	A	C	-	D	A	B	C	-	D	D	A	B	A	A	B	D	-	B	A	A	A	A	-	A	B	-	A	-	A	A			
Fluboric Acid	-	D	B	-	-	D	A	-	-	D	-	A	B	A	B	B	C	-	B	A	-	A	D	-	A	B	-	A	-	-	A			
Fluorine	D	D	D	-	D	D	A	D	-	D	D	C	-	C	-	-	D	-	C	-	-	D	-	-	-	-	-	-	-	-	D			
Fluosilicic Acid	-	-	B	-	D	D	B	-	-	D	-	A	B	A	A	B	D	-	B	A	-	A	D	-	B	A	-	A	-	-	C			
Formaldehyde 40%	-	-	A	-	-	A	A	-	-	-	-	B	-	A	A	-	D	-	-	A	A	-	A	-	D	B	B	A	-	-	A			
Formaldehyde	A	A	A	-	A	A	B	A	B	D	A	A	B	A	D	A	A	-	B	A	A	A	A	-	A	C	B	D	B	C	A			
Formic Acid 6	C	A	B	B	D	C	A	C	C	D	D	D	B	A	A	D	D	-	B	A	A	A	A	B	B	D	C	D	A	C	B			
Freon 11 1	A	-	A	-	B	-	-	B	-	C	B	B	D	A	D	A	A	D	C	-	A	A	A	A	C	C	D	D	D	D	A			
Freon 12 (wet)2	-	-	D	-	B	-	-	B	-	-	-	B	D	A	D	A	A	B	C	A	A	A	A	A	A	A	D	B	B	D	A			
Freon 22	-	-	A	-	B	-	-	B	-	-	-	D	D	-	B	A	A	-	-	-	A	A	A	A	D	D	D	A	A	A	A			
Freon 113	-	-	A	-	B	-	-	B	-	-	-	C	D	-	-	A	A	-	-	-	A	A	A	A	C	A	D	A	-	D	A			
Freon T.F.4	-	-	A	-	B	-	-	B	-	-	-	B	D	-	D	A	A	-	-	D	A	A	A	A	B	A	D	A	D	D	A			
Fruit Juice	A	A	A	A	B	-	-	B	-	D	D	A	-	D	A	B	A	-	B	A	-	A	A	A	A	A	-	A	-	-	A			
Fuel Oils	A	A	A	-	A	A	A	B	-	C	B	A	-	A	A	A	A	-	D	B	A	A	A	-	A	A	C	B	D	D	A			
Furan Resin	-	A	A	-	A	-	-	A	-	A	A	-	-	A	-	A	-	-	-	-	A	-	A	-	A	D	-	D	-	D	A			
Furfural 1	A	A	A	-	A	-	B	A	-	-	A	D	-	A	D	B	A	D	D	D	A	A	A	-	D	D	D	D	B	D	A			
Gallic Acid	B	A	A	-	A	-	A	A	-	D	D	A	A	A	-	-	A	-	-	-	-	-	-	-	B	A	-	-	-	-	-			
Gasoline 1 4	A	A	A	A	A	D	A	A	-	A	A	C	-	A	D	A	A	D	D	C	A	A	A	A	A	D	D	C	D	A	A			
Gelatin	A	A	A	A	A	-	A	A	C	D	D	A	-	A	A	A	A	-	-	A	-	A	A	-	A	A	-	A	A	A	A			
Glucose	A	-	A	-	A	-	-	A	A	B	B	A	B	A	B	A	A	B	B	A	-	A	A	-	A	A	B	A	A	A	A			
Glue P.V.A.1	B	B	A	-	B	A	-	A	-	-	A	A	B	A	-	A	A	-	-	-	-	A	A	-	A	A	-	A	-	-	A			
Glycerine	A	A	A	A	A	A	A	A	B	B	B	A	B	A	A	A	A	C	-	A	-	A	A	-	A	A	B	A	A	A	A			
Cyclic Acid	-	-	-	-	-	-	A	-	-	-	-	A	-	A	C	-	-	B	A	A	A	-	-	A	A	-	A	-	-	A				
Gold Monocyanide	-	-	A	-	-	-	-	A	-	D	-	-	-	-	-	A	-	-	-	-	-	A	A	-	A	A	-	A	-	-	A			
Grape Juice	-	A	A	-	B	-	-	B	-	D	-	A	-	-	A	B	-	B	B	-	-	A	A	-	A	A	-	A	-	-	A			
Grease 4	A	A	A	-	A	-	-	B	-	A	A	-	-	A	-	A	A	-	-	-	-	A	A	-	A	A	-	D	-	-	A			
Heptane 1	A	-	A	-	A	-	-	A	-	-	B	A	-	A	D	A	A	C	D	D	A	A	A	-	A	A	-	B	D	-	A			
Hexane 1	A	A	A	-	A	-	-	A	B	-	-	B	C	-	A	D	A	A	D	-	C	A	A	-	A	A	B	B	D	D	A			
Honey	-	A	A	-	A	-	-	A	-	A	-	A	-	-	A	A	A	B	-	A	-	A	A	-	A	A	-	A	-	-	A			
Hydraulic Oils (Petroleum)1	A	A	A	-	A	-	-	B	-	A	A	-	-	A	-	A	A	-	-	D	-	A	A	-	A	A	-	B	D	D	A			
Hydraulic Oils (Synthetic)1	-	A	A	-	A	-	-	A	-	A	-	-	-	-	-	A	A	-	-	D	-	A	A	-	A	C	D	-	-	-	A			
Hydrazine	-	A	A	-	-	-	-	-	-	C	-	-	-	-	-	D	-	-	-	-	-	A	-	-	A	B	D	B	A	C	A			
Hydrobromic Acid 20%	-	-	D	-	-	A	A	-	-	-	-	A	-	A	A	-	D	-	-	A	-	-	B	-	A	D	-	C	-	-	B			
Hydrobromic Acid 4	D	D	D	D	D	A	A	D	-	D	D	A	B	A	C	D	D	-	B	B	-	A	A	-	A	D	D	D	A	A	A			
Hydrochloric Acid (Dry Gas)	D	C	A	-	D	-	A	-	-	-	D	A	-	A	-	-	-	-	-	-	-	A	-	-	-	-	-	-	-	-	A			
Hydrochloric Acid (20%)4	-	D	D	D	D	C	B	D	-	D	-	A	B	A	A	D	D	B	A	A	D	A	A	D	A	C	-	C	A	C	A			
Hydrochloric Acid (37%)4	-	D	D	D	D	C	B	D	-	D	-	A	B	A	A	D	D	C	A	A	D	A	C	D	A	C	C	C	C	D	A			
Hydrochloric Acid 100%	-	D	D	-	D	D	C	D	-	D	-	A	A	A	-	-	D	-	A	-	-	A	C	-	C	D	-	C	-	-	A			
Hydrocyanic Acid	A	A	A	C	A	A	A	D	D	-	C	A	B	A	A	B	A	-	B	A	-	A	A	-	A	C	-	B	-	-	A	A		
Hydrocyanic Acid (Gas 10%)	-	D	D	-	-	-	-	-	-	-	-	A	-	A	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	C	A	C	A
Hydrofluoric Acid (20%)1	-	D	D	D	D	D	B	D	-	D	-	D	B	A	A	D	D	-	C	A	C	B	C	D	A	D	-	C	A	C	B			
Hydrofluoric Acid (75%) 1 2	-	C	D	-	D	D	C	D	-	D	-	C	B	A	D	D	D	-	C	B	C	D	D	D	A	D	D	D	C	C	C			
Hydrofluoric Acid 100%	D	D	D	-	D	D	B	D	-	D	D	C	D	A	-	-	-	-	D	-	C	D	D	-	-	D	-	D	-	-	D	A		

	302	304	316	440	Aluminium	Titanium	Hastelloy C	Cast Bronze	Brass	Cast Iron	Carbon Steel	PVC (Type 1)	Tygon E-3606	Teflon	Noryl	Polycetal	Nylon	Cyclac (ABS)	Polythylene	Polypropylene	Ryton	Carbon	Ceramic	Ceramagent A	Viton	Buna Nitrile	Silicon	Neoprene	Ethylene P. EPDM	Rubber (Natural)	Epoxy	
Hydrofluosilicic Acid (20%)	-	D	D	-	D	D	B	A	-	D	-	D	-	A	B	D	D	-	-	A	-	A	D	-	A	B	-	B	A	A	C	
Hydrofluosilicic Acid	-	D	D	-	C	-	C	D	-	-	-	-	C	A	-	-	-	-	-	-	-	A	-	-	-	-	D	A	-	-	-	
Hydrogen Gas	A	A	A	-	A	-	-	A	-	B	B	A	-	A	-	-	-	-	-	-	-	-	-	-	A	-	-	-	-	-	A	
Hydrogen Peroxide 10%	-	C	C	-	A	C	A	D	D	D	-	A	A	A	-	-	B	-	A	-	B	A	A	-	A	-	-	D	-	C	D	
Hydrogen Peroxide 30%	-	-	B	-	-	B	A	-	D	-	-	A	-	A	-	-	B	-	-	A	C	-	-	-	A	D	-	C	-	-	B	
Hydrogen Peroxide	-	A	B	A	A	B	A	D	D	D	D	A	C	A	B	D	B	-	B	A	C	-	A	A	A	D	C	D	C	C	A	
Hydrogen Sulfide, Aqueous Solution	-	A	A	C	C	A	A	D	C	D	-	A	B	A	A	D	B	-	B	A	A	A	A	A	A	B	C	-	B	A	D	A
Hydrogen Sulfide (Dry)	A	C	A	-	D	-	A	D	C	B	B	A	-	A	-	-	B	-	-	-	A	-	A	-	A	-	-	-	-	A	A	
Hydroxyacetic Acid (70%)	-	-	-	-	D	B	-	-	-	-	-	A	-	-	-	D	-	-	-	-	-	A	A	-	A	A	-	A	A	-	A	
Ink	A	A	A	-	C	-	-	C	-	D	D	-	-	-	B	A	A	-	B	-	-	A	A	A	A	A	-	A	-	-	A	
Iodine	-	D	D	D	D	A	B	D	-	D	-	D	B	A	A	C	D	D	D	D	-	D	A	-	A	B	-	D	B	D	A	
Iodine (In Alcohol)	-	-	B	-	-	D	A	-	-	-	-	D	-	A	C	-	D	-	-	B	-	-	A	-	A	D	-	D	-	-	-	
Iodoform	B	D	A	-	A	-	-	C	-	C	B	-	-	A	-	-	A	-	-	-	-	-	-	-	C	-	-	-	-	-	-	
Isotane 2	-	-	-	-	A	-	-	-	-	-	-	-	-	-	D	A	-	-	-	D	-	-	A	-	A	A	-	-	-	D	A	
Isopropyl Acetate	-	-	B	-	C	-	-	-	-	-	-	-	-	-	A	-	-	-	-	-	-	A	A	-	D	D	-	D	B	D	A	
Isopropyl Ether 2	A	-	A	-	A	-	-	A	-	-	A	-	-	A	D	A	-	-	D	-	A	A	-	D	B	-	D	D	D	-	-	
Jet Fuel (JP3,JP4,JP5)	A	A	A	-	A	-	-	A	-	A	A	A	-	A	D	A	A	-	-	D	A	A	A	-	A	A	D	D	D	D	A	
Kerosene 2	A	A	A	A	A	A	A	A	A	A	B	A	D	A	D	A	A	B	D	D	A	A	A	A	A	A	D	D	A	D	A	
Ketones	A	A	A	-	B	A	A	A	-	A	A	D	D	A	D	B	A	-	D	D	A	C	A	-	D	D	-	D	D	C	C	
Lacquers	A	A	A	-	A	-	-	A	C	C	C	-	D	-	C	A	A	-	-	A	-	A	A	-	D	D	-	D	-	D	A	
Lacquer Thinners	-	-	A	-	-	A	A	-	C	-	-	C	-	A	D	-	A	-	-	B	-	-	A	-	-	D	-	D	A	-	-	
Lactic Acid	A	A	B	C	C	A	A	D	-	D	D	A	B	A	A	B	C	-	B	A	A	A	A	-	B	B	-	A	B	A	A	
Lard	B	A	A	A	A	-	-	A	-	A	C	A	-	-	-	A	A	C	-	A	-	A	A	-	A	A	C	B	-	D	A	
Latex	-	A	A	-	A	-	-	A	-	-	-	-	-	-	A	A	A	-	B	-	-	-	A	-	A	A	-	C	A	-	A	
Lead Acetate	B	A	A	-	D	A	A	C	-	-	D	A	B	A	A	A	A	-	B	A	-	A	A	-	D	B	-	D	A	A	A	
Lead Sulfamate	-	-	-	-	-	-	-	-	-	-	-	-	-	-	A	-	-	-	A	-	-	-	-	-	A	B	C	A	D	C	A	
Ligroin 3	-	-	A	-	-	-	-	A	-	-	-	-	-	-	D	A	-	-	-	D	-	-	A	-	A	A	-	B	A	D	A	
Lime	-	A	A	-	C	A	-	A	-	A	-	A	-	-	A	D	-	C	-	-	-	A	A	-	A	A	C	B	D	-	A	
Lubricants	-	A	A	-	A	A	A	B	-	-	-	A	-	A	-	A	A	B	-	A	A	A	A	-	A	A	C	D	-	D	A	
Magnesium Carbonate	-	A	A	A	-	-	B	-	-	-	-	A	-	-	A	A	-	-	B	A	-	-	A	-	-	A	-	A	A	-	A	
Magnesium Chloride	B	B	B	A	D	A	A	B	C	D	C	A	B	A	A	A	A	-	B	A	A	-	A	-	A	A	-	A	A	A	A	
Magnesium Hydroxide	A	A	A	-	D	A	A	C	B	B	B	A	-	A	A	A	A	-	B	A	A	A	A	-	A	B	-	B	-	C	A	
Magnesium Nitrate	-	A	A	A	-	A	A	-	-	-	-	A	-	A	A	A	A	-	B	A	-	-	A	-	A	A	-	A	-	-	A	
Magnesium Oxide	-	A	A	-	-	-	-	-	-	-	-	-	-	-	A	-	-	-	-	-	-	-	A	-	-	A	-	A	A	-	A	
Magnesium Sulfate	B	B	A	-	B	A	B	B	B	C	B	A	B	A	A	A	A	-	B	A	A	A	A	-	A	A	-	A	D	C	A	
Maleic Acid	C	A	A	A	B	A	A	C	-	-	B	A	B	A	A	C	A	-	-	C	-	A	A	-	A	D	-	A	D	D	A	
Maleic Anhydride	-	-	-	-	-	-	A	-	-	-	-	-	-	-	-	C	-	-	-	-	-	A	A	-	A	D	-	D	-	D	A	
Malic Acid	B	A	A	-	C	-	A	D	-	-	D	A	-	A	-	-	A	-	-	-	-	-	A	-	C	-	-	A	-	A	-	
Mash	-	A	A	-	-	-	-	A	-	-	-	-	-	-	A	A	-	-	-	-	-	A	A	-	-	A	-	A	-	-	A	
Mayonnaise	A	A	A	-	D	-	-	D	-	D	D	-	-	A	A	A	A	B	-	A	-	A	A	-	A	A	-	-	-	-	A	
Melamine	-	D	D	-	-	-	-	D	-	-	-	-	-	-	-	D	-	-	-	-	-	-	-	-	C	-	-	-	-	-	A	
Mercuric Chloride (Dilute Solution)	D	D	D	D	D	A	B	D	D	D	D	A	A	A	A	A	A	-	B	A	-	A	A	-	A	A	-	A	A	A	A	
Mercuric Cyanide	A	A	A	-	D	A	-	D	-	-	D	A	-	A	A	A	-	-	B	A	-	A	A	-	-	A	-	-	-	-	A	
Mercury	A	A	A	A	C	C	A	D	D	A	A	A	-	A	A	A	A	-	B	A	-	A	A	-	A	A	-	A	A	A	A	
Methanol (See Alcohol Methyl)	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
Methyl Acetate	A	-	A	-	A	-	A	A	-	-	B	-	-	A	-	A	-	D	-	-	-	A	A	-	D	D	D	B	B	D	-	
Methyl Acrylate	-	-	-	-	-	-	-	-	-	-	-	-	-	-	A	-	-	-	-	-	-	-	A	A	-	D	D	-	B	B	D	A
Methyl Acetone	A	-	A	-	A	-	-	A	-	A	A	-	-	A	D	A	-	-	-	-	-	-	A	-	D	D	-	D	-	-	C	
Methyl Alcohol 10%	A	-	A	-	C	-	A	C	-	-	B	A	-	A	-	-	A	-	-	-	-	-	-	-	-	B	-	-	-	A	A	
Methyl Bromide	-	-	-	-	-	-	-	-	-	-	-	-	-	-	A	-	-	-	D	-	-	A	A	-	A	B	-	D	D	D	B	
Methyl Butyl Ketone	-	-	A	-	A	-	-	-	-	-	-	-	-	-	D	B	-	-	-	-	-	A	A	-	D	D	C	D	A	D	B	
Methyl Cellosolve	-	-	-	-	A	-	-	A	-	-	-	-	-	-	C	B	-	-	-	-	-	A	-	A	-	D	D	-	D	B	D	C

	302 Stainless Steel	304 Stainless Steel	316 Stainless Steel	440 Stainless Steel	Aluminium	Titanium	Hastelloy C	Cast Bronze	Brass	Cast Iron	Carbon Steel	PVC (Type 1)	Tygon E-3606	Teflon	Noryl	Polyacetal	Nylon	Cyclac (ABS)	Polyethylene	Polypropylene	Ryton	Carbon	Ceramic	Ceramagent A	Viton	Buna Nitrile	Silicon	Neoprene	Ethylene P. EPDM	Rubber (Natural)	Epoxy	
Methyl Chloride	-	C	A	-	D	A	A	A	-	-	-	D	-	A	D	A	A	-	D	D	-	A	A	-	A	D	D	D	C	D	A	
Methyl Dichloride	-	-	-	-	-	-	-	-	-	-	-	-	-	-	D	A	-	-	-	-	-	A	A	-	A	D	D	D	D	D	A	
Methyl Ethyl Ketone	-	A	A	-	A	A	A	A	-	-	-	D	-	A	D	B	A	D	D	A	A	A	A	-	D	D	C	D	A	D	B	
Methyl Isobutyl Ketone 2	-	-	A	-	-	A	A	-	-	-	-	D	-	A	D	B	A	D	-	C	A	A	A	-	D	D	C	D	C	D	B	
Methyl Isopropyl Ketone	-	-	A	-	-	-	-	-	-	-	-	-	-	-	D	B	A	-	-	-	-	A	A	-	D	D	B	D	B	D	B	
Methyl Methacrylate	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	A	-	-	-	-	-	A	A	-	D	D	-	D	D	D	A	
Methylamine	A	-	A	-	A	-	-	D	-	B	B	-	-	-	B	D	-	-	-	-	-	A	A	-	-	B	-	-	-	-	A	
Methylene Chloride	A	A	A	-	A	A	A	A	C	-	B	D	-	A	D	A	D	-	D	D	-	A	A	-	B	D	-	D	D	D	A	
Milk	A	A	A	A	A	-	-	C	C	D	D	A	-	-	A	A	A	B	B	A	-	A	A	A	A	A	B	A	A	A	A	
Molasses	A	A	A	A	A	-	-	A	B	A	A	A	-	-	B	A	A	-	B	A	-	A	A	A	A	A	-	A	-	-	A	
Mustard	A	A	A	A	B	-	-	B	-	C	B	A	-	-	B	B	A	B	-	A	-	A	A	-	A	B	C	C	-	-	A	
Naptha	A	A	A	A	A	A	A	B	-	B	B	A	C	A	D	A	A	C	D	A	A	A	A	-	A	B	D	D	D	D	A	
Napthalene	B	A	B	-	B	A	A	C	-	B	A	D	-	A	D	A	-	-	D	B	A	A	A	-	C	D	-	D	D	D	A	
Nickel Chloride	-	A	B	-	D	A	A	D	-	D	-	A	B	A	A	B	A	-	B	A	-	A	A	-	A	A	-	A	A	A	A	
Nickel Sulfate	B	A	B	-	D	A	B	C	C	D	D	A	A	A	A	B	A	-	B	A	-	A	A	-	A	A	-	A	A	C	A	
Nitric Acid (10% Solution)	A	A	A	A	D	A	A	D	-	D	D	A	B	A	A	D	D	C	B	A	D	C	B	D	A	D	-	D	B	D	A	
Nitric Acid (20% Solution)	-	A	A	A	D	A	A	D	-	D	-	A	B	A	A	D	D	D	B	A	C	D	C	D	A	D	-	D	D	D	B	
Nitric Acid (50% Solution)	-	A	A	A	D	A	A	D	-	D	-	A	B	A	A	D	D	D	C	D	C	D	A	-	A	D	-	D	D	D	D	
Nitric Acid (Concentrated Solution)	-	D	B	A	B	A	B	D	D	D	-	D	C	A	D	D	D	D	D	D	C	D	A	C	B	D	-	D	D	D	D	
Nitrobenzene 2	B	A	B	-	C	A	B	D	-	B	B	D	D	A	D	B	C	D	D	C	B	A	A	-	D	D	D	D	D	D	D	B
Oils																																
Aniline	-	A	A	-	C	A	D	A	-	A	-	D	-	A	D	D	C	D	-	A	-	A	A	-	A	D	-	D	B	D	A	
Anise	-	A	A	-	-	-	-	-	-	-	-	-	-	-	-	A	-	-	-	-	-	A	A	-	-	-	-	D	-	-	A	
Bay	-	A	A	-	-	-	-	-	-	-	-	-	-	-	-	A	-	-	-	-	-	A	A	-	A	-	D	-	-	A		
Bone	-	A	A	-	-	-	-	A	-	-	-	-	-	-	-	A	-	-	-	-	-	A	A	-	A	A	-	D	-	-	A	
Castor	-	A	A	-	A	-	-	A	-	A	-	A	-	-	-	A	-	-	-	-	-	A	A	A	A	A	-	A	B	A	A	
Cinnamon	-	A	A	-	-	-	-	-	-	-	-	-	-	A	-	A	-	-	-	-	-	A	A	-	D	-	-	D	-	-	A	
Citric	-	A	A	-	-	-	-	D	-	D	-	-	-	-	-	A	A	-	-	-	-	A	A	-	A	A	-	D	-	-	A	
Clove	-	A	A	-	-	-	-	-	-	-	-	-	-	-	-	A	A	-	-	B	-	A	A	-	-	A	-	-	-	-	A	
Coconut	-	A	A	-	B	-	-	A	-	A	-	-	-	-	-	A	A	-	-	-	-	A	A	-	A	A	-	A	A	D	A	
Cod Liver	-	A	A	-	B	-	-	-	-	-	-	-	-	-	-	A	A	C	-	A	-	A	A	-	A	A	-	B	A	D	A	
Corn	-	A	A	A	B	-	-	B	-	A	-	-	-	-	-	A	A	C	-	A	-	A	A	-	A	A	-	D	C	D	A	
Cotton Seed	B	A	A	A	B	-	-	B	-	A	C	A	-	A	-	A	A	C	-	A	A	A	-	A	A	-	D	C	D	A		
Cresote 2	-	A	A	-	A	-	-	-	-	-	-	-	-	-	D	-	-	-	D	-	A	A	-	A	A	-	B	D	D	A		
Diesel Fuel (2D,3D,4D,5D)	-	A	A	-	A	-	-	A	-	-	-	-	-	-	D	A	A	-	-	-	-	A	A	-	A	A	-	D	D	D	A	
Fuel (1,2,3,5A,5B,6)	-	A	A	-	A	A	A	A	-	-	-	A	-	A	D	A	-	-	-	B	-	A	A	-	A	B	-	D	D	D	A	
Ginger	-	A	A	-	-	-	-	-	-	-	-	-	-	-	-	A	-	-	-	-	-	A	A	-	A	A	-	A	-	-	A	
Hydraulic (See Hydraulic)	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
Lemon	-	A	A	-	-	-	-	-	-	-	-	-	-	-	-	A	-	-	-	-	D	-	A	A	-	A	-	D	-	-	A	
Linseed	-	A	A	A	A	-	-	A	-	A	-	A	B	-	-	A	A	C	-	A	-	A	A	A	A	A	-	D	D	D	A	
Mineral	A	A	A	A	A	-	-	A	-	A	B	A	-	-	B	A	A	-	-	B	A	A	A	A	A	A	-	B	D	D	A	
Olive	A	A	A	-	A	-	-	B	-	A	B	A	-	A	-	A	A	-	-	-	-	A	A	-	A	A	C	B	-	D	A	
Orange	-	A	A	-	-	-	-	-	-	-	-	-	-	-	A	-	A	A	-	-	-	-	A	A	-	A	-	D	-	-	A	
Palm	-	A	A	-	A	-	-	B	-	-	-	-	-	-	-	A	A	-	-	-	-	A	A	-	A	A	-	D	-	-	A	
Peanut 3	-	A	A	-	A	-	-	A	-	A	-	A	-	-	-	A	-	-	-	D	-	A	A	-	A	A	-	D	-	D	A	
Peppermint 2	-	A	A	-	-	-	-	A	-	-	-	-	-	-	-	A	-	-	-	D	-	A	A	-	A	D	-	D	-	-	A	
Pine	A	A	A	-	A	-	-	D	-	C	B	A	-	A	-	A	-	-	-	-	-	-	A	A	-	A	-	D	-	D	A	
Rape Seed	-	A	A	-	-	-	-	A	-	-	-	-	-	-	-	A	-	-	-	-	-	-	A	A	-	A	B	-	D	-	D	A
Rosin	-	A	A	-	A	-	-	-	-	-	-	-	-	-	-	A	A	-	-	-	-	-	A	A	-	A	-	-	-	-	A	
Sesame Seed	-	A	A	-	A	-	-	A	-	A	-	A	-	-	-	A	-	-	-	-	-	-	A	A	-	A	-	D	-	-	A	
Silicone	-	A	A	-	-	-	-	A	-	A	-	-	-	-	-	A	A	A	-	-	-	-	A	A	A	A	-	A	-	-	A	
Soybean	-	A	A	-	A	-	-	B	-	A	-	A	-	-	-	A	A	-	-	-	-	-	A	A	-	A	-	D	-	D	A	

	302 Stainless Steel	304 Stainless Steel	316 Stainless Steel	440 Stainless Steel	Aluminium	Titanium	Hastelloy C	Cast Bronze	Brass	Cast Iron	Carbon Steel	PVC (Type 1)	Tygon E-3606	Teflon	Noryl	Polycetal	Nylon	Cyclac (ABS)	Polyethylene	Polypropylene	Ryton	Carbon	Ceramic	Ceramagent A	Viton	Buna Nitrile	Silicon	Neoprene	Ethylene P. EPDM	Rubber (Natural)	Epoxy
Sodium Acetate	B	A	A	B	B	A	A	B	-	C	C	A	-	A	A	B	A	-	B	A	-	A	A	-	D	D	-	C	-	A	A
Sodium Aluminate	B	-	-	A	C	B	B	B	-	-	C	-	-	A	A	B	A	-	-	-	A	A	A	-	A	A	-	A	A	B	A
Sodium Bicarbonate	B	A	A	A	A	A	-	B	A	C	C	A	B	A	A	B	A	B	B	A	A	A	A	A	A	A	C	A	A	A	A
Sodium Bisulfate	A	A	-	A	D	B	B	C	C	D	D	A	B	A	A	B	C	C	B	A	A	A	A	-	B	A	C	A	-	A	A
Sodium Bisulfite	-	A	-	A	A	A	B	C	-	D	-	A	B	A	A	B	D	B	B	A	A	A	A	-	A	A	C	A	-	A	A
Sodium Borate	B	A	-	A	C	-	A	A	-	C	C	C	-	A	-	-	A	-	A	-	-	-	-	-	A	-	B	A	-	-	-
Sodium Carbonate	B	A	B	B	C	A	A	B	B	B	B	A	B	A	A	A	A	C	B	A	A	B	A	-	A	A	-	A	A	A	A
Sodium Chlorate	B	A	-	A	B	A	B	B	-	-	C	A	B	A	A	D	A	-	B	A	A	A	A	-	A	D	-	A	-	A	A
Sodium Chloride	B	A	C	B	C	A	A	B	C	B	C	A	B	A	A	A	A	B	B	A	A	A	A	A	A	A	C	A	A	B	A
Sodium Chromate	A	A	A	-	D	-	B	B	-	B	B	-	-	A	A	D	A	-	-	A	A	A	B	-	B	A	-	A	-	-	C
Sodium Cyanide	B	A	-	A	D	A	-	D	D	B	B	A	-	A	A	D	C	-	B	A	A	A	A	-	A	A	D	A	A	A	A
Sodium Fluoride	B	C	-	C	C	A	A	C	-	D	D	D	D	A	-	-	A	-	C	-	-	-	-	-	C	D	-	D	-	D	A
Sodium Hydrosulfite	-	-	-	-	A	-	A	C	-	-	-	C	A	A	-	-	A	-	-	-	-	-	A	-	A	-	-	A	-	A	-
Sodium Hydroxide (20%)	-	A	A	A	D	A	A	C	D	A	-	A	B	A	A	D	C	C	B	A	A	C	D	A	A	A	D	B	A	A	A
Sodium Hydroxide (50% Solution)	-	A	B	-	D	A	A	C	D	B	-	A	B	A	A	D	C	C	C	A	B	C	D	A	A	D	D	C	-	A	A
Sodium Hydroxide (80% Solution)	-	A	D	-	D	A	B	C	D	C	-	A	B	A	A	D	C	C	C	A	B	C	D	A	B	D	D	C	-	B	A
Sodium Hypochlorite 3 (to 20%)	-	C	C	C	C	A	A	D	D	D	-	A	B	A	A	D	A	-	B	D	C	D	A	B	A	C	D	D	B	C	B
Sodium Hypochlorite	D	-	A	-	D	A	A	D	-	D	D	A	-	A	A	-	A	-	-	A	C	-	D	-	D	B	C	A	-	-	A
Sodium Hyposulfate	-	A	A	-	D	-	-	D	-	-	-	-	-	A	-	-	-	-	-	-	-	-	-	-	-	-	-	C	-	C	C
Sodium Metaphosphate 2	A	-	A	-	A	-	-	C	C	B	B	-	-	A	-	B	A	-	-	D	-	A	A	-	A	A	-	B	A	A	A
Sodium Metasilicate	A	-	A	-	B	-	-	B	-	C	C	-	-	A	-	D	-	-	-	-	-	A	-	-	A	A	D	A	-	-	A
Sodium Nitrate	B	A	A	A	A	A	B	B	C	A	B	A	B	A	A	B	A	-	B	A	-	A	A	B	C	D	B	A	C	A	A
Sodium Perborate	B	-	C	-	B	-	-	C	C	B	B	-	-	A	A	B	A	-	-	A	-	A	A	-	A	B	D	B	A	C	A
Sodium Peroxide	B	A	A	-	C	-	B	C	C	D	C	A	-	A	-	D	D	-	-	-	-	A	A	-	A	C	D	B	A	C	A
Sodium Polyphosphate	-	A	A	-	D	A	A	C	-	-	-	-	-	A	A	B	-	-	-	-	-	A	A	-	A	A	-	D	A	A	A
Sodium Silicate	B	A	B	A	C	A	B	C	C	-	B	A	B	A	A	C	A	-	-	A	-	A	A	-	A	A	-	A	A	A	A
Sodium Sulfate	B	A	A	C	B	A	B	B	B	A	B	A	-	A	A	B	A	-	B	A	A	A	A	-	A	A	-	A	A	C	A
Sodium Sulfide	B	A	B	-	D	A	B	D	D	A	B	A	B	A	A	B	A	-	B	A	A	A	A	-	A	C	-	A	A	C	A
Sodium Sulfite	-	C	C	-	C	A	A	C	-	A	-	A	A	A	-	-	D	-	A	-	-	A	A	-	A	A	-	A	-	A	A
Sodium Tetraborate	-	-	A	-	-	-	-	-	-	-	-	A	-	-	A	B	-	-	-	-	-	A	A	-	A	A	-	-	-	-	A
Sodium Thiosulphate ("Hypo")	A	A	A	-	B	A	-	D	D	C	B	A	-	A	A	C	A	-	-	A	A	A	-	A	B	-	A	A	C	A	A
Sorghum	-	A	A	-	-	-	-	-	A	-	-	-	-	-	A	A	-	-	-	-	-	A	A	-	A	A	-	A	-	-	A
Soy Sauce	-	A	A	-	A	-	-	A	-	D	-	-	-	-	A	A	A	-	-	-	-	A	A	-	A	A	-	A	-	D	A
Stannic Chloride	D	D	D	-	D	A	B	D	-	D	D	A	-	A	A	C	A	-	B	A	-	-	A	-	A	A	D	A	A	A	A
Stannic Fluoborate	-	-	A	-	-	-	-	-	D	-	-	-	-	-	A	C	-	-	A	-	-	-	A	-	A	A	-	A	-	-	A
Stannous Chloride	D	D	C	-	D	A	A	D	-	D	D	A	A	A	-	-	D	-	A	-	-	-	-	-	B	C	D	D	-	A	A
Starch	B	A	A	-	A	-	-	B	-	C	C	A	-	A	A	A	A	-	B	-	-	A	A	-	A	A	-	A	-	-	A
Stearic Acid 2	B	A	A	A	B	A	A	C	C	C	C	A	B	A	A	A	A	-	B	D	-	A	A	A	A	B	D	B	B	C	A
Stoddard Solvent	A	A	A	A	A	A	A	A	A	B	B	A	D	A	D	A	A	B	D	D	A	A	A	-	A	B	D	D	D	D	A
Styrene	A	A	A	-	A	-	-	A	-	-	A	-	-	A	A	A	-	-	-	-	-	A	A	-	B	D	D	D	D	D	A
Sugar (Liquids)	A	A	A	A	A	-	A	A	-	B	B	-	-	A	A	A	A	B	-	A	-	A	A	A	A	A	-	B	-	A	A
Sulfate Liquors	-	C	C	-	B	-	A	C	-	-	-	-	-	-	-	D	-	-	-	A	-	A	A	-	-	-	-	C	-	-	A
Sulfur Chloride	-	D	D	D	D	-	-	C	D	-	-	A	C	A	A	D	A	-	A	D	-	A	C	-	A	D	-	D	D	D	C
Sulfur Dioxide 2	-	A	A	C	A	A	B	B	-	-	-	D	B	A	D	B	D	D	C	D	A	A	A	-	D	D	C	B	A	D	A
Sulfur Dioxide (Dry)	A	A	A	-	A	-	A	A	C	A	B	D	-	A	-	-	A	-	D	-	-	A	A	-	A	-	-	D	-	D	D
Sulfur Trioxide (Dry)	A	A	C	-	A	-	-	B	-	B	B	A	B	A	D	D	D	-	-	-	-	B	A	-	A	D	-	D	B	C	A
Sulfuric Acid (to 10%)	-	D	C	C	C	A	A	D	D	D	-	A	B	A	A	D	D	B	B	A	A	A	A	-	A	C	-	D	D	C	A
Sulfuric Acid (10%-75%) 2	-	D	D	D	D	C	B	D	D	D	-	A	B	A	B	D	D	B	C	A	B	A	D	C	A	D	-	D	D	D	B
Sulfuric Acid 75%-100%	-	-	D	-	-	D	B	-	D	-	-	B	-	A	A	-	D	-	-	B	C	-	A	-	A	D	-	D	-	-	D
Sulfurous Acid	C	C	B	C	C	A	B	D	-	D	D	A	B	A	A	D	D	-	B	A	-	B	A	-	A	C	D	B	B	C	A
Sulfuryl Chloride	-	-	-	-	-	-	-	-	-	-	-	A	-	A	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	A
Syrup	-	A	A	A	A	-	-	D	-	-	-	A	-	-	A	A	A	B	-	A	-	A	A	A	A	-	B	-	A	A	

	302 Stainless Steel	304 Stainless Steel	316 Stainless Steel	440 Stainless Steel	Aluminium	Titanium	Hastelloy C	Cast Bronze	Brass	Cast Iron	Carbon Steel	PVC (Type 1)	Tygon E-3606	Teflon	Noryl	Polycetal	Nylon	Cyclac (ABS)	Polythylene	Polypropylene	Ryton	Carbon	Ceramic	Ceramagent A	Viton	Buna Nitrile	Silicon	Neoprene	Ethylene P. EPDM	Rubber (Natural)	Epoxy
Tallow	-	A	A	-	A	-	-	-	-	-	-	-	-	-	A	A	A	-	C	-	-	A	A	-	A	A	-	-	-	-	A
Tannic Acid	B	A	A	A	C	A	B	B	-	C	C	A	B	A	A	B	D	-	B	A	-	A	A	A	A	D	C	A	A	A	A
Tanning Liquors	-	A	A	-	C	A	A	A	-	-	-	A	B	A	-	B	-	-	-	A	-	A	A	-	A	C	-	-	-	-	A
Tartaric Acid	B	A	B	B	C	A	B	A	C	D	D	A	B	A	A	B	A	-	B	A	-	A	A	-	A	D	C	A	-	A	A
Tetrachlorethane	-	-	A	-	-	A	A	-	-	-	-	D	-	A	D	A	A	-	-	A	-	A	A	-	A	D	-	-	D	D	A
Tetrahydrofuran	-	A	A	-	D	-	-	D	-	D	A	D	-	A	D	A	A	-	D	C	A	A	A	-	B	D	-	D	B	D	A
Toluene, Toluol 3	A	A	A	-	A	A	A	A	A	A	A	D	D	A	D	A	A	D	D	D	A	A	A	A	C	D	D	D	D	D	A
Tomato Juice	A	A	A	-	A	-	-	C	-	C	C	-	-	A	A	B	A	B	-	A	A	A	A	-	A	A	-	A	-	-	A
Trichlorethane	-	C	A	-	C	A	A	C	-	C	-	-	-	A	D	A	-	-	-	-	-	A	A	-	A	D	D	D	D	D	A
Trichlorethylene 2	B	A	A	-	B	A	A	B	A	C	B	D	-	A	D	A	C	D	D	D	C	A	A	C	A	D	D	D	D	D	A
Trichloropropane	-	-	A	-	-	-	-	A	-	-	-	-	-	-	D	A	-	D	-	-	-	A	A	-	A	A	-	A	-	-	A
Tricresylphosphate	-	-	A	-	-	B	A	A	-	-	-	D	-	A	A	C	-	-	-	-	-	A	A	-	B	D	-	D	A	-	A
Triethylamine	-	-	-	-	-	-	-	A	-	-	-	A	-	-	B	D	-	-	-	-	-	A	A	-	A	A	D	B	-	-	A
Turpentine 3	B	A	A	-	C	-	A	B	C	B	B	A	B	A	D	A	A	-	D	B	A	A	A	-	A	D	-	D	D	D	A
Urine	-	A	A	-	B	-	-	C	-	B	-	A	-	-	A	A	A	-	B	A	-	A	A	-	A	A	-	D	A	-	A
Vegetable Juice	-	A	A	-	A	-	-	C	-	D	-	-	-	-	A	A	A	-	-	-	-	A	A	-	A	A	B	D	-	D	A
Vinegar	A	A	A	A	D	A	A	B	B	C	D	A	-	A	A	B	A	B	B	A	A	A	A	A	A	C	-	B	A	C	A
Varnish (Use Vitonic for Aromatic)	A	A	A	A	A	-	-	A	B	-	C	-	-	A	D	A	A	-	-	A	-	A	A	A	A	B	C	D	-	D	A
Water, Acid , Mine	-	A	A	-	C	-	-	C	D	C	-	A	B	-	A	D	A	B	-	A	B	A	A	-	A	A	-	B	-	B	A
Water, Distilled , Lab Grade 7	-	A	A	-	B	-	-	A	-	D	-	A	B	A	A	A	A	A	-	A	A	A	A	A	A	A	-	B	A	A	A
Water, Fresh	A	A	A	-	A	-	-	A	C	B	D	A	B	A	A	A	A	A	D	A	A	A	A	A	A	A	-	B	A	A	A
Water, Salt	-	A	A	-	B	-	-	B	C	D	-	A	B	-	A	A	A	-	-	A	A	A	A	A	A	A	-	B	A	A	A
Weed Killers	-	A	A	-	C	-	-	C	-	-	-	-	-	-	-	A	A	-	-	-	-	A	A	-	A	B	-	C	-	-	A
Whey	-	A	A	-	B	-	-	-	-	-	-	-	-	-	-	A	-	-	-	-	-	A	A	-	A	A	-	-	-	-	A
Whiskey and Wines	A	A	A	A	D	-	-	B	B	D	D	A	-	A	A	A	A	-	B	A	-	A	A	-	A	A	B	A	A	A	A
White Liquor (Pulp Mill)	-	A	A	-	-	-	A	D	-	C	-	A	-	A	A	D	A	-	-	A	-	A	A	-	A	A	-	A	-	-	A
White Water (Paper Mill)	-	A	A	-	-	-	-	A	-	-	-	-	-	-	-	B	A	-	-	A	-	A	A	-	A	-	-	A	-	-	A
Xylene 2	A	A	A	-	A	-	A	A	A	A	B	D	-	A	D	A	A	D	D	D	A	A	A	A	A	D	D	D	D	D	A
Zinc Chloride	D	A	B	B	D	A	B	D	D	D	D	A	-	A	A	C	A	-	B	A	A	A	A	-	A	A	-	A	A	A	A
Zinc Hydrosulphite	-	-	A	-	D	-	-	D	-	D	-	-	-	-	A	C	-	-	-	-	A	A	A	-	-	A	-	A	A	-	A
Zinc Hydrosulfate	B	A	A	A	D	A	B	B	C	C	D	C	B	A	A	C	A	-	B	A	A	A	A	-	A	A	-	A	A	C	A
Zinc Sulfate	B	A	A	A	D	A	B	B	C	C	D	C	B	A	A	C	A	-	B	A	A	A	A	-	A	A	-	A	A	C	A